

# **BLANK PAGE**



## Indian Standard

METHODS OF TEST FOR STYRENE-BUTADIENE RUBBER (SBR) LATICES

PART 1 DETERMINATION OF DRY POLYMER CONTENT

SBRL:1

(First Revision)

UDC 678.746.22-136.22:543.814



@ Copyright 1986

INDIAN STANDARDS INSTITUTION
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

## Indian Standard

## METHODS OF TEST FOR STYRENE-BUTADIENE RUBBER (SBR) LATICES

#### PART 1 DETERMINATION OF DRY POLYMER CONTENT

#### SBRL:1

## (First Revision)

#### Rubber Sectional Committee, PCDC 14

Chairman

Representing

SHRI LALIT MOHAN JAMNADAS

Cosmos India Rubber Works Pvt Ltd, Bombay

Vice-Chairman

Dunlop India Ltd, Calcutta

Members

SHRI S. B. GANGULY

SHRI K. S. LOGANATHAN ( Alternate to

Shri S. B. Ganguly )

SHRI SATISH ABRAHAM SHRI O. P. AGARWAL

Padinjarekara Agencies Ltd, Kottayam Transasia Carpets Ltd, Sikandrabad

SHRI J. N. JHA ( Alternate )

Ministry of Defence (DGI)

SHRI A. K. BANDOPADHAYA

SHRI V. BHATTACHARYA ( Alternate )

DR B. BANERJEE

DR D. BANERJEE

Carbon and Chemicals India Ltd, Cochin

Escon Consultants Pvt Ltd, Calcutta

DR P. S. BHARGAVA

Alkali and Chemical Corporation of India Ltd,

Calcutta

SHRI N. C. SAMAJDAR ( Alternate )

SHRI J. CHATTERJEE Andrew Yule & Co Ltd. Calcutta

SHRI-A. K. BISWAS ( Alternate )

All India Rubber Industries Association, Bombay

SHRI P. K. CHATTERJEE

DR S. N. CHAKRAVARTY ( Alternate ) Synthetics and Chemicals Ltd, Bombay

SHRI H. C. CHOPRA

DR R. N. MEHROTRA ( Alternate ) Association of Planters of Kerala, Cochin

SHRI D. W. McCRIRICK

SHRI P. K. MENON ( Alternate )

National Test House, Calcutta

DR D. K. DAS

SHRI A. GHOSH ( Alternate )

SHRI P. B. G. DASTIDAR SHRIS. SARKAR ( Alternate ) Bata India Ltd, Calcutta

SHRI S. L. GANDHI

Ministry of Defence (R & D) SHRI H. C. PERTI ( Alternate )

(Continued on page 2)

#### © Copyright 1986

#### INDIAN STANDARDS INSTITUTION

This publication is protected under the Indian Copyright Act (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

#### IS: 4511 ( Part 1 ) - 1986

(Continued from page 1)

Members

Representing

SHRI J. M. GARG

Directorate General of Technical Development,

New Delhi

SHRI A. GEORGE JOHN

MRF Ltd, Madras

SHRI K. J. JOSEPH Pla SHRI K. T. VERGHESE ( Alternate )

Plantation Corporation of Kerala Ltd, Kottayam

SHRI G. R. KAVISHVAR

Indian Rubber Regenerating Co Ltd, Thane

SHRI P. S. VIRANI ( Alternate ) SHRI K. N. KOSHY

M. M. Rubber Co Ltd, Madras

SHRI N. SUBRAMANIAN ( Alternate )

Thirumbadi Rubber Ltd, Mokkam

SHRI P. K. MADHAVA MENON SHRI M. PUSHKARAKSHAN ( Alternate )

SHRI L. K. MATHUR

Modi Rubber Ltd, Modipuram

SHRI P. K. MENON

United Planters' Association of Southern India, Coonoor

SHRI E. B. UNNI ( Alternate )

DR W. MILLINS

Indian Rubber Manufacturers' Research Association, Thane

SHEI N. B. FEGADE ( Alternate ) SHRI R. MURLEEDHARAN NAIR

Hindustan Latex Ltd, Trivandrum Bayer (India) Ltd, Bombay

SHRI R. R. PANDIT SHEI D. J. BHARUCHA ( Alternate )

SHRI S. A. PASHA

London Rubber Co ( India ) Ltd, Madras

SHRI R. KRISHNAN ( Alternate ) SHRI M. C. PAUL

Arakkunnam Cooperative Rubber Marketing Society Ltd. Arakkunnam

SHRI A. RAJAMANI

Tyre Manufacturers' Association, Automotive New Delhi

SHRI A. GEORGE JOHN ( Alternate )

Tyre Corporation of India Ltd, Calcutta

DR S. K. RAY SHRI S. B. SARKAR ( Alternate )

Travancore Rubber & Tea Co Ltd, Trivandrum

SHRI S. V. SARMA SHRI C. S. KRISHNASWAMY ( Alternate )

Ltd. Indian Petrochemicals Corporation

SHRI SUNIL I. SHAH

Director (P & C)

Jawaharnagar

SHRI A. K. MALLIK ( Alternate ) SHRI RAJINDER SINGH SHRI O. P. ARORA ( Alternate )

State Trading Corporation of India Ltd, Bombay Rubber Research Institute of India, Kottayam; and

DR E. V. THOMAS DR M. G. KUMARAN ( Alternate I )

Rubber Board, Kottayam

DR N. M. MATHEW ( Alternate II ) SHRI M. S. SAXENA.

Director General, ISI (Ex-officio Member)

Secretary

SHRI DILEEP KUMAR Assistant Director (P&C), ISI

(Continued on page 10)

### Indian Standard

# METHODS OF TEST FOR STYRENE-BUTADIENE RUBBER (SBR) LATICES

# PART 1 DETERMINATION OF DRY POLYMER CONTENT SBRL: 1

(First Revision)

#### O. FOREWORD

**6.1** This Indian Standard (Part 1) (First Revision) was adopted by the Indian Standards Institution on 14 February 1986, after the draft finalized by the Rubber Sectional Committee had been approved by the Petroleum, Coal and Related Products Division Council.

**0.2** Test methods for rubber latex had been originally covered in the following Indian Standards:

For natural rubber latex

IS: 3708 (Part 1)-1966\*
IS: 3708 (Part 2)-1968†
For styrene-butadiene rubber latex
IS: 4511 (Part 1)-1967‡

Since some of the test methods covered in these standards were common, the concerned committee had decided to unify and publish a separate series of methods of test which would be applicable to all types of latices — natural as well as synthetic. Accordingly, the following six test methods had been covered in the following different parts of IS: 9316:

IS: 9316 Methods of test for rubber latex:

Part 1-1979 Determination of surface tension

†Methods of test for natural rubber latex: Part 2 Determination of boric acid and magnesium.

<sup>\*</sup>Methods of test for natural rubber latex: Part 1 Dry rubber content, sludge content, density, total alkalinity, KOH-number, mechanical stability, volatile fatty acid number, pH, total nitrogen, total copper, total iron, total maganese and total ash.

<sup>‡</sup>Methods of tests for styrene-butadiene rubber (SBR) latices: Part 1 Determination of dry polymer, pH, density, residual styrene, bound styrene and soap content.

#### IS: 4511 (Part 1) - 1986

Part 2-1979 Determination of viscosity

Part 3-1979 Determination of coagulum content

Part 4-1979 Determination of total solids content

Part 5-1979 Drawing of samples

Part 6-1982 Determination of pH

- 0.2.1 As a result of further rethinking on the subject, it has now been decided to re-designate the test methods common to natural and synthetic rubber latices as RL series; test methods for natural rubber latex as NRL series and test methods for styrene-butadiene rubber latex as SBRL series. Consequently, test methods for rubber latex have been rationalized into the following three series:
  - a) IS: 9316 Unified methods of test applicable to both natural and synthetic rubber latices — RL series:
  - b) IS: 3708 Methods of test applicable to natural rubber latex NRL series; and
  - c) IS: 4511 Methods of test applicable to styrene-butadiene rubber latex - SBRL series.
- 0.3 The existing Indian Standards IS: 3708 (Part 1)-1966\*, IS: 3708 (Part 2)-1968†, IS: 4511 (Part 1)-1967‡, IS: 9316 (Parts 1 to 5)-19798 and IS: 9316 (Part 6)-1982 are being gradually replaced by separate standards under the above three series, designated as NRL, SBRL, or RL series, respectively.
- 0.3.1 The methods covered under NRL: 13, NRL: 14 and NRL: 15 of IS: 3708 (Part 1)-1966\* which are also under revision, have been proposed to be covered under the RL series in IS: 9316 (under revision).
- 0.4 In order to facilitate cross-reference, it has been decided to retain. in the revisions of various parts of IS: 4511, the original discrete SBRL series numbers assigned to various test methods earlier in IS: 4511 ( Part 1 )-1967‡.

†Methods of test for natural rubber latex: Part 2 Determination of boric acid and magnesium.

Part 1 Determination of surface tension.

Part 2 Determination of viscosity.

Part 3 Determination of coagulum content.

Part 4 Determination of total solids content.
Part 5 Drawing of samples.

<sup>\*</sup>Methods of test for natural rubber latex: Part 1 Dry rubber content, sludge content, density, total alkalinity, KOH-number, mechanical stability, volatile fatty acid number. oH, total nitrogen, total copper, total iron, total manganese and total ash.

Methods of tests for styrene-butadiene rubber (SBR) latices: Part 1 Determination of dry polymer, pH, density, residual styrene, bound styrene and soap content. §Methods of test for rubber latex:

<sup>||</sup> Methods of test for rubber latex: Part 6 Determination of pH.

- **0.4.1** For proper referencing of the existing test methods and the new methods under revision, a statement showing corresponding methods is given in Appendix A.
- **0.5** In reporting the result of a test or analysis made in accordance with this standard, if the final value, observed or calculated, is to be rounded off, it shall be done in accordance with IS: 2-1960\*.

#### 1. SCOPE

1.1 This standard (Part 1) prescribes the procedure for determination of dry polymer content of styrene-butadiene rubber latices.

#### 2. OUTLINE OF THE METHOD

2.1 Latex is coagulated by isopropanol. The coagulum is refluxed, washed, dried and weighed.

#### 3. APPARATUS

- 3.1 Air Oven maintained at 105 ± 2°C.
- 3.2 Desiccator
- 3.3 Flask 250-ml or 500-ml capacity with ground glass neck of at least 50 mm diameter.
- 3.4 Measuring Cylinder 100-ml capacity.
- 3.5 Nylon Gauze 105 microns.
- 3.6 Reflux Condenser all glass with ground glass joints.
- 3.7 Steam Bath
- 3.8 Watch Glass
- 3.9 Weighing Bottle with Close Fitting Stopper
- 4. REAGENT
- 4.1 isoPropanol conforming to IS: 2631-1976.

#### 5. PROCEDURE

**5.1** Take the seived original latex in dry prepared (at  $105 \pm 2^{\circ}$ C) weighing bottle and transfer 5 to 7 g of latex by difference of mass, to the nearest 1 mg, in a small beaker (100 ml) and dilute it to

<sup>\*</sup>Rules for rounding off numerical values ( revised ).

<sup>†</sup>Specification for isopropyl alcohol (first revision).

#### IS: 4511 ( Part 1 ) - 1986

approximately 25 to 30 percent with distilled water. Pour the diluted latex in thin stream into a flask (500 ml) containing 100 ml of isopropanol. Rinse the beaker with distilled water and transfer to the flask. Attach the reflux condenser to the flask and reflux on the steam bath for one hour. Remove the flask from the steam bath and decant the solvent into a beaker covered with fine gauze, taking care that the minimum amount of coagulum is decanted with the solvent. Return any coagulum from the gauze to the flask, add 100 ml of distilled water to the flask and shake vigorously. Decant the water through the same gauze and repeat the procedure with 100 ml of fresh water until no more foam is obtained (three or four washings may be sufficient). Wash the decanted coagulum in the flask with 100 ml solvent and the coagulum into the gauze. Carefully transfer the coagulum to pretared watch glass and dry at 105 ± 2°C in the air oven. Cool in a desiccator to room temperature and weigh. Repeat drying and weighing till the dried mass is constant to 0.000 2 g.

**5.2** If duplicate determinations do not agree within 0.2 percent 'dry polymer, make additional duplicate determinations until such agreement is obtained.

#### 6. CALCULATION

6.1 Calculate the dry rubber content as follows:

Dry polymer content,

percent by mass = 
$$\frac{M_1}{M_2} \times 100$$

where

 $M_1$  = mass in g of dried coagulum, and  $M_2$  = mass in g of the original latex.

( Clause 0.4.1 )

TABLE SHOWING CORRESPONDENCE OF VARIOUS METHODS OF TEST COVERED IN THE EXISTING IS: 9316 (PARTS 1 TO 5)-1979, IS: 9316 (PART 6)-1982, IS: 3708 (PART 1)-1966, IS: 3708 (PART 2)-1968, IS: 4511 (PART 1)-1967, WITH THE REVISION/PROPOSED REVISION OF IS: 9316, IS: 3708 AND IS: 4511

Existing Test Methods			PROPOSED REVISION		Remarks
Test Method	IS No. (2)	Part (Series) (3)	IS No. (4)	Part ( Series ) (5)	(6)
RL SERIES					
Determination of sur- face tension	IS: 9316-1979	Part 1	IS:9316	Part 1 (RL:1)	
Determination of visco- sity	IS: 9316-1979	Part 2	IS: 9316	Part 2 (RL:2)	
Determination of coagulum content	IS: 9316-1979	Part 3	IS: 9316	Part 3 (RL:3)	
Determination of total solids content	IS: 9316-1979	Part 4	IS: 9316	Part 4 (RL:4)	Under
Drawing of samples	IS: 9316-1979	Part 5	IS:9316	Part 5 (RL:5)	revision
Determination of pH	IS: 9316-1982	Part 6	IS:9316	Part 6 (RL:6)	
Determination of total copper	IS: 3708-1966	Part 1 (NRL: 13)	IS: 9316	Part 7 (RL:7)	
Determination of total			IS:9316	Part 8 (RL:8)	
Determination of total manganese	IS: 3708-1966	Part 1 (NRL: 15)	IS:9316	Part 9 (RL:9)	
3					(Continued)

S: 4511 ( Part 1 ) - 198

TABLE SHOWING CORRESPONDENCE OF VARIOUS METHODS OF TEST COVERED IN THE EXISTING IS: 9316 (PARTS 1 TO 5)-1979, IS: 9316 (PART 6)-1982, IS: 3708 (PART 1)-1966, IS: 3708 (PART 2)-1968, IS: 4511 (PART 1)-1967, WITH THE REVISION/PROPOSED REVISION OF IS: 9316, IS: 3708 AND IS: 4511 — Contd

Existing Test Methods			Proposed Revision		REMARKS
Test Method (1)	IS No. (2)	Part ( Series ) (3)	IS No. (4)	Part ( Series ) (5)	<b>(</b> 6)
NRL SERIES	(2)	(3)	(1)	(0)	(0)
Determination of dry rubber content	IS: 3708-1966	Part 1 (NRL:1)	IS: <b>3708</b> -1985	Part 1 (NRL:1)	)
Determination of sludge content	IS: 3708-1966	Part 1 (NRL:5)	IS: 3708-1985	Part 2 ( NRL: 5)	۲
Determination o density	IS: 3708-1966	Part 1 (NRL:6)	IS: 3708-1985	Part 3 ( NRL: 6	)
Determination of total alkalinity	IS: 3708-1966	Part 1 (NRL:7)	IS: 3708-1985	Part 4 (NRL:7)	
Determination of KOH- number	IS: 3708-1966	Part 1 (NRL:8)	IS: 3708-19 <b>8</b> 5	Part 5 ( NRL : 8	)
Determination of mechanical stability	IS: 3708-1966	Part 1 (NRL:9)	IS: 3708-1985	Part 6 (NRL:9)	
Determination of vola- tile fatty acid number	IS: 3708-1966	Part 1 (NRL:10)	IS: 3708-1985	Part 7 (NRL: 10	)
Determination of total nitrogen	IS: 3708-1966	Part 1 (NRL:12)	IS: 3703-1985	Part 8 ( NRL: 12	)
Determination of total ash	IS: 3708-1966	Part 1 (NRL: 16)	IS: <b>37</b> 08-19 <b>8</b> 5	Part 9 (NRL:16	)

œ

Determination of boric acid	IS: 3708-1968	Part 2 (NRL: 17)	IS: 3708	Part 10 (NRL:17)	
Determination of mag- nesium	IS: 3708-1968	Part 2 (NRL: 18)	IS: 3708	Part 11 (NRL: 18)	)
SBRL SERIES					
Determination of dry polymer	IS: 4511-1967	Part 1 (SBRL:1)	IS: 4511	Part 1 (SBRL:1)	
Determination of density	IS: 4511-1967	Part 1 (SBRL:6)	IS:4511	Part 2 (SBRL: 6)	
Determination of residual styrene (volatile unsaturates)	IS: 4511-1967	Part 1 (SBRL:8)	IS; 4511	Part 3 (SBRL:8)	Under Revision
Determination of bound styrene	IS:4511-1967	Part 1 (SBRL:9)	IS:4511	Part 4 (SBRL:9)	
Determination of soap content	IS: 4511-1967	Part 1 (SBRL:10)	IS: 4511	Part 5 (SBRL: 10)	Under Revision

9

#### IS: 4511 ( Part 1 ) - 1986

(Continued from page 2)

#### Methods of Testing Subcommittee, PCDC 14:1

Convener

Representing

Dr S. N. CHAKRAVARTY

Modi Rubber Ltd, Modipuram

Members

SHRI S. K. MUSTAFI ( Alternate to

Dr S. N. Chakravarty )

SHRI SATISH ABRAHAM

SHRI P. S. BALASUBRAMANIAM

SHRI S. KUMAR ( Alternate ) SHRI A. N. BHATTACHARYA

L. G. Balakrishnan & Bros Ltd, Coimbatore

Union Commercial & Industrial Co Pvt Ltd,

SHRI B. PANJA ( Alternate ) SHRI J. CHATTERJEE

SHRI A. K. BISWAS ( Alternate )

SHRI P. K. CHATTERJEE

SHRI D. J. BHARUCHA ( Alternate )

SHRI H. C. CHOPRA DR R. N. MEHROTRA ( Alternate )

SHRI J. M. GARG

SHRI K. R. GARG SHRI P. L. NAG ( Alternate )

SHRI C. S. INAMDAR

SHRI V. K. SUD ( Alternate )

SHRI A. GEORGE JOHN

SHRI G. R. KAVISHVAR SHRI P. S. VIRANI ( Alternate )

SHRI P. L. KINARIWALA

SHRI S. N. GHADGE ( Alternate ) SHRI K. S. LOGANATHAN

DR S. CHATTOPADHYAY ( Alternate ) SHRI P. K. MADHAVA MENON

SHRI A. K. MALLIK

DR Y. N. SHARMA ( Alternate ) DR W. MILLINS

SHRI ASOK MITRA

DR S. K. RAY ( Alternate ) Shri P. K. Pain

SHRI S. V. SARMA

SHRI C. S. KRISHNASWAMY ( Alternate ) SHRI E. V. THOMAS

Padinjarekara Agencies Ltd, Kottayam

Calcutta

Directorate General of Technical Development.

Andrew Yule & Co Ltd, Calcutta

Bayer (India) Ltd, Bombay

Synthetics & Chemicals Ltd, Bombay

New Delhi

Ministry of Defence (DGI)

Polyolefins Industries Ltd, Bombay

MRF Ltd, Madras

Indian Rubber Regenerating Co Ltd, Bombay

Cosmos India Rubber Works Pvt Ltd, Bombay

Dunlop India Ltd, Calcutta

Thirumbadi Rubber Co Ltd, Mokkam

Petrochemicals Corporation Ltd. Indian Jawaharnagar

Indian Rubber Manufacturers' Research Association, Thane

Tyre Corporation of India Ltd, Calcutta

National Test House, Calcutta

Travancore Rubber & Tea Co Ltd, Trivandrum

Rubber Board, Kottayam

DR N. M. MATHEW ( Alternate )



# INDIAN STANDARDS INSTITUTION

### Headquarters:

THE PERSON OF TH	Manak Bhavan	9 Bahadur	Shah Zafar Mai	g. NEW DELHI	110002
--	--------------	-----------	----------------	--------------	--------

Telephones: 331 0131	331 1375	Telegrams : Manaksanstha
		/ Common to all Offices

( Common to	
Regional Offices:	Telephone
*Western : Manakalaya, E9 MIDC, Marol Andheri (East) BOMBAY 400093	6 32 92 95
†Eastern : 1/14 C. I. T. Scheme VII M, V. I. P. Road, Maniktola, CALCUTTA 700054	36 24 99
Northern: SCO 445-446, Sector 35-C CHANDIGARH 160036	{ 2 18 43 3 16 41
Southern : C. I. T. Campus, MADRAS 600113	{ 41 24 42 41 25 19 41 29 16
Branch Offices:	
Pushpak', Nurmohamed Shaikh Marg, Khanpur AHMADABAD 380001	{ 2 63 48 2 63 49
'F' Block, Unity Bldg, Narasimharaja Square, BANGALORE 560002	22 48 05
Gangotri Complex, 5th Floor, Bhadbhada Road, T. T. Nagar, BHOPAL 462003	6 67 16
Plot No. 82/83, Lewis Road, BHUBANESHWAR 751002	6 36 27
53/5 Ward No. 29, R. G. Barua Road, 5th Byelane, GUWAHATI 781003	-
5-8-56C L. N. Gupta Marg, HYDERABAD 500001	22 10 83
R14 Yudhister Marg, C Scheme, JAIPUR 302005	{ 6 34 71 6 98 32
117/418 B Sarvodaya Nagar, KANPUR 208008	{21 68 76 21 82 92
Patliputra Industrial Estate, PATNA 800013	6 23 05
Hantex Bldg (2nd Floor), Rly Station Road, TRIVANDRUM 695001	62 27
Inspection Office (With Sale Point):	
Institution of Engineers (India) Building, 1332 Shivaji Nagar, PUNE 411005	5 24 35
*Sales Office in Bombay is at Novelty Chambers, Grant Road. BOMBAY 400007	89 65 28
†Sales Office In Calcutta Is at 5 Chowringhee Approach. P.O. Princep Street, CALCUTTA 700072	27 68 00